

**■ THERMAL**

Property	Method	Units	QUINN XT
Vicat temperature (B 50)*	ISO 306	°C	105
Specific heat capacity	ISO 11357-4	J/gK	1.47
Linear thermal expansion	DIN 53752	K <sup>-1</sup> ×10 <sup>-5</sup>	7
Thermal conductivity	DIN 52612	W/mK	0.18
Service temperature continuous use		°C	70
Max. temperature short term use		°C	90
Degradation temperature		°C	>280